

Experimental XZ 93081.00

Trinseo - Polycarbonate + ABS

Friday, May 8, 2020

General Information

Product Description

XZ 93081.00 (future PULSE™ GX70 ECO) is a developmental PC/ABS blend which contains >50% industrial recycled polymer (PIR). A high quality and consistency level like for the standard Pulse™ GX70 is achieved for this resin. It combines consistent and easy processability with good low temperature impact resistance. The heat resistance is tailor made to resist most automotive interior and exterior component requirements. The grade is only available in standard black.

This technical data sheet and the product data it contains, are linked to a potential future commercial Trinseo product name.

General

Generic Name	• Polycarbonate + ABS (PC+ABS)
Material Status	• INTERNAL ONLY
Availability	• Europe

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	15	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	2150	MPa	ISO 527-2
Tensile Stress ³ (Yield)	49.0	MPa	ISO 527-2
Tensile Strain ³ (Break)	> 80	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	50	kJ/m ²	
23°C	55	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	98.0	°C	ISO 75-2/A
Vicat Softening Temperature	118	°C	ISO 306 ⁴
CLTE - Flow (23 to 55°C)	8.0E-5	cm/cm/°C	ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
Burning Rate	35	mm/min	ISO 3795

Processing Information

Injection	Nominal Value	Unit
Melt Temperature (Aim)	275	°C
Mold Temperature	70	°C

Experimental XZ 93081.00

Trinseo - Polycarbonate + ABS

www.ulprospector.com

Friday, May 8, 2020

Notes

¹ Typical properties: these are not to be construed as specifications.

² 1 mm/min

³ 50 mm/min

⁴ 50°C/h, B (50N)