

MAGNUM™ 3325 MT

ABS Resin

Trinseo

PROSPECTOR®

www.ulprospector.com

Technical Data

Product Description

Overview:

MAGNUM™ 3325MT is a medium heat ABS. Its inherent low gloss combined with a high flow makes it specifically suitable for unpainted interior automotive applications. It is globally available, locally produced in major car production regions.

Benefits:

- Lot to lot consistency allowing for optimal machine parameters settings from the start
- Self-coloring enabling improvement of costs by using less pigments and lowering your logistic costs
- Low VOC allowing a better interior air quality facing increasing regulatory and OEMs constraints.
- Heat stability during wide range of processing temperatures: enhanced part design freedom
- High scratch and mar resistance for an improved aesthetic durability of the parts
- Easier recyclability of unpainted part

Applications:

- Matt/unpainted interior automotive applications
- Mid-consoles
- Pillars
- Door Trims
- Glove boxes"

General

Material Status	• Commercial: Active		
Literature ¹	• Brochure - MAGNUM™ ABS - Tthe Benchmark ABS for Extrusion (English) • Brochure - MAGNUM™ ABS Resins - Proven to enhance productivity and efficiency (English) • Press Release - Trinseo broadens Plastic Resin offering in North America (English) • Technical Datasheet		
Search for UL Yellow Card	• Trinseo • MAGNUM™		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Features	• Good Processability	• Medium Heat Resistance	• Medium Impact Resistance
Uses	• Automotive Applications	• Automotive Interior Trim	
Forms	• Pellets		
Processing Method	• Injection Molding		

Physical	Nominal Value Unit	Test Method
Density	1.05 g/cm³	ISO 1183
Apparent (Bulk) Density	0.65 g/cm³	ISO 60
Melt Mass-Flow Rate (MFR)		ISO 1133
220°C/10.0 kg	10 g/10 min	
230°C/3.8 kg	2.8 g/10 min	
Molding Shrinkage	0.40 to 0.70 %	ISO 294-4
Mechanical	Nominal Value Unit	Test Method
Tensile Modulus	1850 MPa	ISO 527-1/1
Tensile Stress (Yield)	38.0 MPa	ISO 527-2/50
Tensile Strain		ISO 527-2/50
Yield	3.0 %	
Break	20 %	
Flexural Modulus ³	1850 MPa	ISO 178
Flexural Stress ³	58.0 MPa	ISO 178



MAGNUM™ 3325 MT

ABS Resin

Trinseo

PROSPECTOR®

www.ulprospector.com

Impact	Nominal Value Unit	Test Method
Charpy Notched Impact Strength 23°C, Injection Molded	16 kJ/m ²	ISO 179/1eA
Notched Izod Impact Strength -30°C	10 kJ/m ²	ISO 180/1A
23°C	17 kJ/m ²	
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	79.0 °C	ISO 75-2/A
Vicat Softening Temperature	99.0 °C	ISO 306/B50
Flammability	Nominal Value Unit	Test Method
Carbon Emission ⁴	35.0 µg/g	VDA 277
Injection	Nominal Value Unit	
Drying Temperature	80 to 90 °C	
Drying Time	2.0 to 4.0 hr	

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.

³ 2.0 mm/min

⁴ This rating not intended to reflect hazards presented by this or any other material under actual fire conditions.



Where to Buy**Supplier****Trinseo**

, USA

Telephone: 888-789-7661**Web:** <http://www.trinseo.com/>**Distributor****Avient Distribution***Avient Distribution is a global distribution company. Contact Avient Distribution for availability of individual products by country.***Telephone:** +1-440-930-3004 (USA); +86-21-6028-4805 (China)**Web:** <https://now.avient.com/>**Availability:** Global**Channel Prime Alliance****Telephone:** 800-247-8038**Web:** <http://www.channelpa.com/>**Availability:** North America**Entec Polymers****Telephone:** 833-319-0299**Web:** https://www.entecpolymers.com/?utm_source=ul&utm_medium=paid%20association&utm_campaign=entec%20%7C%20entec%201&utm_term=ul%20%7C%20where%20to%20buy**Availability:** North America**Entec Polymers Latin America***Contact Entec Polymers for availability of individual products by country.***Web:** <https://www.entecpolymers.com/>**Availability:** Latin America**Nexeo Plastics - Europe***Nexeo Plastics is a Pan European distribution company. Contact Nexeo for availability of individual products by country.***Telephone:** +34-93-480-9125**Web:** <https://www.nexeoplastics.com/>**Availability:** Austria, Belgium, Bulgaria, Czech Republic, Denmark, Finland, France, Germany, Ireland, Italy, Latvia, Lithuania, Luxembourg, Netherlands, Norway, Poland, Portugal, Romania, Russian Federation, Slovakia, Spain, Sweden, Switzerland, United Kingdom**Osterman & Company****Telephone:** 800-914-4437**Web:** <http://www.osterman-co.com/>**Availability:** North America**PolySource***PolySource is a North American resin and plastics distributor. Please feel to reach out to your Technical Sales Account Manager. <https://polysource.net/our-team/>***Telephone:** 866-558-5300**Web:** <http://www.polysource.net/>**Availability:** North America**RESINEX Group***RESINEX is a Pan European distribution company. Contact RESINEX for availability of individual products by country.***Telephone:** +32-14-672511**Web:** <http://www.resinex.com/>**Availability:** Europe**Tex-Co Resin Distribution, Inc.****Telephone:** 877-908-3926**Web:** <http://www.texcoresin.com/>**Availability:** North America