

Technical Data

产品说明

PULSE™ 120 PC/ABS resin delivering optimized performance for automotive interior component application

Benefits

- High-impact strength even at low temperature
- Middle Heat resistance for demanding automotive interior components
- Consistent natural white color produces high quality part appearance when used with color concentrates (self coloring) or Trinseo Color Masterbatch Technology
- Low odor & VOC to meet all global Automotive OEM specifications

Applications

- Mid (floor)consoles
- Instrument Panel components
- Door panel trim
- Pillars
- Storage / load floors / glove box

总览

材料状态	• 已商用：当前有效		
资料 ¹	• Technical Datasheet		
搜索 UL 黄卡	• Trinseo • PULSE™		
供货地区	• 亚太地区		
特性	• 高抗撞击性 • 良好的加工性能	• 耐低温冲击 • 韧性良好	
用途	• 汽车领域的应用	• 汽车内部零件	• 汽车仪表盘
形式	• 粒子		

物理性能	额定值 (英制)	额定值 (公制)	测试方法
密度 / 比重			
--	1.13	1.13 g/cm ³	ASTM D792
--	1.13 g/cm ³	1.13 g/cm ³	ISO 1183
熔流率 (熔体流动速率) (260°C/5.0 kg)	18 g/10 min	18 g/10 min	ISO 1133
机械性能	额定值 (英制)	额定值 (公制)	测试方法
拉伸模量	305000 psi	2100 MPa	ISO 527-1/1
拉伸应力 (屈服)	7980 psi	55.0 MPa	ISO 527-2/50
拉伸应变			ISO 527-2/50
屈服	4.0 %	4.0 %	
断裂	120 %	120 %	
弯曲模量 ³	290000 psi	2000 MPa	ISO 178
弯曲应力 ³	11600 psi	80.0 MPa	ISO 178
冲击性能	额定值 (英制)	额定值 (公制)	测试方法
简支梁缺口冲击强度			ISO 179/1eA
-22°F (-30°C)	19 ft-lb/in ²	40 kJ/m ²	
73°F (23°C)	26 ft-lb/in ²	55 kJ/m ²	
热性能	额定值 (英制)	额定值 (公制)	测试方法
载荷下热变形温度 (264 psi (1.8 MPa), 未退火)	212 °F	100 °C	ISO 75-2/A
维卡软化温度	253 °F	123 °C	ISO 306/B50



注射	额定值 (英制)	额定值 (公制)
干燥温度	212 °F	100 °C
干燥时间	4.0 hr	4.0 hr
加工 (熔体) 温度	491 到 536 °F	255 到 280 °C
模具温度	140 到 176 °F	60 到 80 °C

备注

¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。

² 一般属性：这些不能被视为规格。

³ 0.079 in/min (2.0 mm/min)



购买地点

供应商

Trinseo
, USA
电话: 888-789-7661
Web: <http://www.trinseo.com/>

分销商

请联系供应商以便为 PULSE™ 120 查找分销商

