

Ecotran[®] E2130TM

Polyphenylene sulfide

Outline : Ecotran E2130TM is a 30% glass fiber filled PPS compound developed to provide high toughness

	Method	Unit	E2130TM NC	E2130TM BK
General Information			GF 30% Super tough	GF 30% Super tough
Physical properties				
Density	ISO 1183/A	kg/cm ³	1,490	1,490
Water absorption	ISO 62	%	0.02	0.02
Mold shrinkage (MD/TD)	ISO 294-4	%	0.3 / 0.8	0.3 / 0.8
Mechanical properties				
Tensile strength	ISO 527-1, -2	MPa	160	155
Flexural strength	ISO 178	MPa	238	235
Flexural modulus	ISO 178	MPa	8,800	8,800
Flexural elongation at break	ISO 178	%	3.10	3.00
Charpy impact strength (notched)	ISO 179	kJ/m ²	12	11.5
Charpy impact strength (unnotched)	ISO 179	kJ/m ²	68	67
Thermal properties				
Melting temperature	ISO 11357	°C		280
Heat Deflection temperature, 1.82Mpa	ISO 75-1, -2/A	°C		265
Flammability (T=3.2mm)	UL 94	class		V-0
Processing Conditions				
Pre-drying		-		130°C / 4hr
Cylinder temperature		°C		280 - 330
Mold temperature		°C		130 - 150

* The information provided in this data sheet is based on SK's knowledge and test method, it can not be used as guaranteed specification limits.



