



# Zhuhai Sumika Polymer Compounds Co.,Ltd.

NO.3210,Zhufeng Avenue South,Doumen District,Zhuhai City,Guangdong Province,China  
〒519-175 TEL:(86)756-6318788 FAX:(86)756-6318789  
The Garden Tower 1234-1237,368 Huanshi Dong Lu,Guangzhou ,Guangdong Province,China  
〒510-064 TEL:(86) 20-83652567 FAX:(86) 20-83652797

## F611X99 BLACK 物性表

### The Physical Properties of F611X99 BLACK

| No. | 项 目<br>Item                                    | 测定方法<br>Test Methods   | 单 位<br>Unit (Si) | 条 件<br>Conditions | 物性值<br>Values |
|-----|------------------------------------------------|------------------------|------------------|-------------------|---------------|
| 1   | 比 重<br>Specific Gravity                        | ISO 1183 A             | —                | —                 | 1.12          |
| 2   | 熔融流动指数<br>Melt Flow Rate                       | ISO 1133               | g/10min.         | 230℃              | 12            |
| 3   | 拉伸屈服强度<br>Tensile Strength at Yield            | ISO 527-1,-2           | MPa              | —                 | 114           |
| 4   | 拉伸破坏伸度<br>Tensile Elongation of Break          |                        | %                |                   | 3.1           |
| 5   | 拉伸模量<br>Tensile Modulus                        |                        | MPa              |                   | 7700          |
| 6   | 弯曲强度<br>Flexural Strength                      | ISO 178                | MPa              | —                 | 150           |
| 7   | 弯曲模量<br>Flexural Modulus                       |                        | MPa              | —                 | 6500          |
| 8   | CHARPY缺口冲击强度<br>Charpy Impact Notched Strength | ISO 179                | kJ/m2            | 23℃               | 10            |
| 9   | CHARPY冲击强度<br>Charpy Impact Unnotched Strength | ISO 179                | kJ/m2            | 23℃               | 58            |
| 10  | 热变形温度<br>Heat Deflection Temperature           | ISO 75-1,-2            | ℃                | 1.8 MPa           | 150           |
| 11  | 灰 分<br>Ash Content                             | 住化法<br>Sumitomo Method | %                | —                 | 30            |

备注：

Remarks：

1、一般物性在没有要求前提下，都是通过射出成型试验片，并在 23℃条件下测定的。

All measurement on injection molded samples and testing at 23℃.

2、本物性表数据非规格值。

This data is not standard values.



## Zhuhai Sumika Polymer Compounds Co.,Ltd.

NO.3210,Zhufeng Avenue South,Doumen District,Zhuhai City,Guangdong Province,China  
〒519-175 TEL:(86)756-6318788 FAX:(86)756-6318789  
The Garden Tower 1234-1237,368 Huanshi Dong Lu,Guangzhou ,Guangdong Province,China  
〒510-064 TEL:(86) 20-83652567 FAX:(86) 20-83652797

### 3、Technical Information

#### PRE-DRYING REQUIREMENTS

|                                              | Units  | Values             |
|----------------------------------------------|--------|--------------------|
| Pre-Drying Required?                         | –      | Yes                |
| Storage Life (Unopened) @ 23° C/50% R.H.     | Months | 6                  |
| Open Storage Time Before Pre-Drying Required | Hours  | 6                  |
| Pre-Drying Recommendation                    | –      | 3-4 Hours at 90° C |

#### PROCESSING GUIDELINES

| Processing Parameter                        | Units       | Recommendation    |
|---------------------------------------------|-------------|-------------------|
| Barrel Temperature Profile (Rear to Nozzle) | °C          | 200,230, 240, 250 |
| Injection Speed                             | –           | Medium to Fast    |
| Use of Back Pressure                        | Bar         | Low               |
| Tool Temperature Requirement                | °C          | 30 – 60           |
| Regrind Addition (Maximum)                  | % by Weight | 10                |

SPECIALIST PROCESSING ADVICE IS AVAILABLE FROM TECHNICAL DEPARTMENT

#### HEALTH & SAFETY DATA

|                                  | Units   | Recommendation                |
|----------------------------------|---------|-------------------------------|
| Maximum Barrel Residence Time    | Minutes | 15                            |
| Maximum Barrel Temperature       | °C      | 280                           |
| Spontaneous Ignition Temperature | °C      | 320                           |
| Disposal of Purgings and Melts   | –       | Cooled in Water to Avoid Fire |

A Separate Material Safety Data Sheet Is Also Available

Issue No : 02  
Data Issued : 2017/8/24