

ECOTRIA

CLARO100-CR50



Product description

SK chemicals chemical recycling solution utilizes chemically recycled raw materials to deliver the same level of physical properties as existing copolyesters. ECOTRIA CLARO-CR is a copolyester designed to be fully compatible with PET recycling stream and containing chemically recycled contents. It is a suitable and clear copolyester in a variety of consumer product applications, including food & beverage packaging, general purpose packaging, flexible film packaging, and consumer products. ECOTRIA CLARO-CR meet the definition of PET as ASTM-D7611-20 with the resin identification

Applications

- Cosmetic Packaging
- Home Appliance
- Consumer Goods

Key Attributes

- PCR Material (50%)
- recyclable with the PET stream
- Chemical Resistance High Flowability
- Transparency
- Ability to mold thick Parts
- Excellent processing capability
- Low Crystallinity

Notes

The data listed here is preliminary data sheet of product. Therefore this sheet should not be used to establish specification limits or used alone as a basis for design. This information is not intended as a warranty of any kind. Customers must make their own representative test and assume all risks of use, whether used alone or in combination with other products. SK Chemicals assumes no obligation or liability of any advice furnished by it or results obtained with respect to these products. All warranties of merchantability for a particular purpose or use are excluded and disclaimed.

Typical properties for

ECOTRIA CLARO100-CR50

ASTM Method

Product Information

Property 属性	Test Method 测试方法	Unit 单位	Result 值
Specific Gravity 比重	ASTM D792	-	1.32
Mold Shrinkage 模具收缩率	ASTM D955	%	0.2 ~ 0.5
Rockwell Hardness 洛氏硬度	ASTM D785	R-scale	105
Tensile Strength @ Yield 屈服拉伸强度	ASTM D638	Kgf/cm ²	500
Tensile Strength @ Break 断裂拉伸强度	ASTM D638	Kgf/cm ²	260
Elongation @ Yield 屈服伸长率	ASTM D638	%	4.1
Elongation @ Break 断裂伸长率	ASTM D638	%	95
Flexural Strength 弯曲强度	ASTM D790	Kgf/cm ²	740
Flexural Modulus 弯曲模量	ASTM D790	Kgf/cm ²	20,800
Izod Impact Strength Notched @ 23 °C Izod缺口冲击强度@23 °C	ASTM D256	J/m	80
Heat Distortion Temperature @ 0.455 MPa / @1.820 MPa 热变形强度 @ 0.455 MPa / @ 1.820 MPa	ASTM D648	°C	68 / 60
Haze 雾度	ASTM D1003	%	< 1.0
Transmittance 透光率	ASTM D1003	%	89

Headquarter / R&D center

310 Pangyo-ro, Bundang-gu, Seongnam-si,
Gyeonggi-do, Republic of Korea [13494]
TEL : +82-2-2008-2008
FAX : +82-2-2008-2009

Ulsan Plant

718, Cheoyong-ro, Nam-gu, Ulsan, Republic
of Korea [44784]
TEL : +82-52-256-0121
FAX : +82-52-256-0652

The information in this data sheet is, to the best of our knowledge, true and accurate. The representations about the product are based upon test results achieved under laboratory practices supervised and controlled by SK chemicals corporation.

Typical properties for

ECOTRIA

CLARO100-CR50

ISO
Method

Product Information

Property 属性	Test Method 测试方法	Unit 单位	Result 值
Specific Gravity 比重	ISO 1183	-	1.32
Mold Shrinkage 模具收缩率	D955	%	0.2 ~ 0.5
Rockwell Hardness 洛氏硬度	ISO 2039-2	R-scale	105
Tensile Strength @ Yield 屈服拉伸强度	ISO 527	MPa	49
Tensile Strength @ Break 断裂拉伸强度	ISO 527	MPa	25
Elongation @ Yield 屈服伸长率	ISO 527	%	4.0
Elongation @ Break 断裂伸长率	ISO 527	%	49
Flexural Strength 弯曲强度	ISO 178	MPa	67
Flexural Modulus 弯曲模量	ISO 178	MPa	1,760
Izod Impact Strength Notched @ 23 °C Izod缺口冲击强度@23 °C	ISO 180	KJ/m2	7.1
Heat Distortion Temperature @ 0.455 MPa / @ 1.820 MPa 热变形强度@ 0.455 MPa / @ 1.820 MPa	ISO 75	°C	68 / 61
Haze 雾度	D1003	%	< 1.0
Transmittance 透光率	D1003	%	89

Headquarter / R&D center

310 Pangyo-ro, Bundang-gu, Seongnam-si,
Gyeonggi-do, Republic of Korea [13494]
TEL : +82-2-2008-2008
FAX : +82-2-2008-2009

Ulsan Plant

718, Cheoyong-ro, Nam-gu, Ulsan, Republic
of Korea [44784]
TEL : +82-52-256-0121
FAX : +82-52-256-0652

The information in this data sheet is, to the best of our knowledge, true and accurate. The representations about the product are based upon test results achieved under laboratory practices supervised and controlled by SK chemicals corporation.