

技术数据表
Technical Data Sheet (TDS)

第 1 页/共 3 页

优能胶 HAN65B2
EMPILON® HAN65B2

➤ 说明 Description:

特性 Features	● 优能胶 HA 系列产品主要是与工程塑料射出(注塑)接着, 如 ABS、PC…等, 具有极佳的触感、雾面的质感、减震止滑…等特性的热可塑性弹性材料。 EMPILON® HA series product are specially designed for over-molding with engineering plastics such as ABS, PC etc, for soft touch, anti-slip, and vibration functional purposes.
外观 Appearance	● 黑色 加钾长石 8% Black add potash feldspar 8% ● 圆柱形或椭圆形的颗粒 Cylindrical or elliptic pellet
包装 Packaging	● 25 公斤/袋 25 kg/bag
储存 Storage	● 常温下, 保存在阴凉, 通风良好的干燥处, 约 12 个月。 Keep in a cold, well-ventilated dry place at normal temp, about 12 months.
用途 Application	● 3C 电子产业、工具握把等。 3C industry, hand held device products etc.
状态 Status	● 符合 RoHS 规范要求 Complies with RoHS requirements ● 符合 EU REACH 任一项高关注物质(SVHC)要求 Complies with EU REACH for any SVHCs requirement ● 不含卤素有害物质 Free of Halogen

技术数据表

Technical Data Sheet (TDS)

第 2 页/共 3 页

➤ 物性 Physical properties:

项目 Item	测试法 Method	单位 Unit	HAN65B2
比重 Specific gravity	ASTM D792	--	1.16
硬度 Hardness	ASTM D2240	<1 sec. shore A	75
硬度 Hardness	ASTM D2240	10 sec. shore A	67
抗张强度 Tensile strength	ASTM D412	kgf/cm ²	60
接着强度(ABS) ABS Adhesion	HT Method	kgf/2.5cm	10
接着强度(PC) PC Adhesion	HT Method	kgf/2.5cm	12
伸长率 Elongation at break	ASTM D412	%	450
流动指数 Melt index	ASTM D1238	g/10min	G 6
脆化温度 Brittle temp.	估计值 Estimate	°C	-40
收缩率 Shrinkage (参考用) (reference only)	平行 Machine direction	%	0.7
	垂直 Transverse direction	%	1.3

☆ 流动指数: G 为 200°C/5 kg 测试条件。

Melt index : G means the condition 200°C/5 kg

➤ 使用法 Usage:

射出(注塑)机 Injection machine	大多数聚烯烃系能使用的射出机均能使用 Most olefin plastic machines can be used for injection molding.
射出机压缩比 Compression ratio	> 2.4 2.4 and higher
胶粒干燥 Drying	使用除湿干燥机 80~90°C, 至少 2 小时以上干燥, 射出(注塑)其间仍需持续干燥 Pellets need 80~90 °C dehumidified hot air at least 2 hours before any molding process and need to be continually dried during operation.
清洗料管 Purge compound	聚丙烯 PP 塑料 Polypropylene (PP)
回收 Recycling	二次料(水口料)回收比率建议最多 5% Consistent regrind usage of up to 5% is permissible.
着色 Coloring	请选择以 PE 或 EVA 为基材之色母, 切勿使用以 PVC 为基材者。另外加工时请采用较高的螺杆转速和较高的背压, 才能让着色剂达到较好的分散效果。 Please select color master batch on PE or EVA material with the exception of PVC. Higher screw speed and backpressure are needed for better colorant dispersion.

技术数据表

Technical Data Sheet (TDS)

第 3 页/共 3 页

➤ 成型条件 Injection molding parameters:

● 料管温度	cylinder temperatures	
✧ 进料段	feed zone	180~190 °C
✧ 中间段	center zone	185~200 °C
✧ 出料前段	front zone	195~205 °C
✧ 射嘴	nozzle	200~220 °C
● 模温	mold temperature	30~50 °C
● 射出压力	injection pressure	35~50 kgf/cm ²
● 射速	injection rate	适当 / moderate
● 保压时间	hold time	5 sec.
● 螺杆转速	screw speed	中速 / medium
● 背压	back pressure	5~10 kgf/cm ²
● 循环时间	cycle time	15~30 sec.
(厚度小于 2mm 物件) (goods material thickness under 2mm)		

☆ 正确的熔融温度为 180°C~220°C，勿超过 240°C。

Please maintain the material melt temp. around 180°C to 220°C during processing, but not exceeding 240°C.

➤ 注意 Notes:

- 以上数据由和泰实验室提供，各项物性数据并不作为产品规格表使用，仅供参考。
Data is provided by HOTAI laboratory. Properties are not to be constructed as specification.

網站 Web site : www.empilon.com

和泰股份有限公司

HO TAI INDUSTRIAL CO., LTD.

台灣桃園市新屋區中山東路二段 352 號

No.352, Sec. 2, Zhongshan E. Rd., Xinwu Dist., Taoyuan City 32741, Taiwan

Tel : 886-3-4904506

Fax : 886-3-4905106

寧波廠/寧波優能塑料科技

NINGBO EMPILON PLANT

中國浙江寧波經濟技術開發區大港五路 39 號

No. 39, Da Gang 5th Rd., Da Gang Industrial City, Ningbo Economic & Technical Development Zone, Beilun, Ningbo, P.R.C.

Tel : 86-574-86809800

Fax : 86-574-86809819

深圳公司/深圳市東積架新材料科技有限公司

SHENZHEN BRANCH

中國廣東深圳市寶安區福永街道橋頭社區福霖大廈 14 樓

Room 14/F, Fulin Buiding qiaotou village Fuyong Town Baoan District Shenzhen, Guangdong, P.R.C.

Tel : 86-755-23156909

Fax : 86-755-23156929