

Technical Data sheet

Genestar G1350A – M42 Black

Genestar G1350A-M42 is a 35% glass reinforced injection grade. This grade was developed specifically for improved performance in a 50/50 ethylene glycol and water environment.

Main feature of G1350A-M42 are;

- Hydrolysis resistance
- Heat resistance
- Chemical resistance

Examples of application are;

- Thermostat housings
- Water inlets, outlets, and valves

	Units	Test Method ISO	Value
GF Content	%	—	35
Physical properties			
Specific gravity	—	1183	1.40
Water absorption (23°C, in water, 24hrs)	%	62	0.19
Mechanical properties			
Tensile strength	MPa	527	200
Tensile elongation at break	%	527	2.5
Flexural strength	MPa	178	285
Flexural modulus	GPa	178	10.0
Charpy impact strength, Notched	kJ/m ²	179/1eA	12
Thermal properties			
Melting point	°C	11357-3	300
Glass Transition Temperature	°C	—	125
DTUL(1.82MPa)	°C	75Af	270
Dimensional properties			
Mold shrinkage MD	%	294-4	0.3
TD	%	294-4	0.9
Abrasion properties			
Critical PV value	kg/cm ² · cm/sec		N/A
Coefficient of Friction	P=10kg f /cm ²	JIS K7218-A	N/A
Wear	P=10kg f /cm ²	mg	N/A

*Values shown in above table are typical values, not specified values.

To the best of our knowledge, information contained herein is accurate. It is the sole responsibility of the customer to determine whether the product is appropriate and suitable for customer's specific use. Specific end use may require approval by appropriate regulatory agencies. Kuraray makes no warranties, express or implied, regarding products on any information contained here in. Kuraray disclaims any liability for infringement of any patent by reason of customer's use of any Kuraray products in combination with other materials or in any process.

December/2012