

Dryflex FSC0609

General

Description	Thermoplastic Elastomer, TPS-SEBS
Colour	Black
Form	Free flowing pellets
Service Temperature	-50 to +125°C (unstressed material)
Recycling	100% recyclable

Typical Properties

Property	Units	Typical Value	Test Method
Hardness	Shore A	65	ASTM D2240 ¹
Density	g/cm ³	0.97	ASTM D792
Tensile Strength	MPa	5	ASTM D412
Modulus 100%	MPa	1.5	ASTM D412
Modulus 300%	MPa	2.5	ASTM D412
Elongation at Break	%	500	ASTM D412
Tear Strength	N/mm	31	ASTM D624 Method B

¹ After 15 seconds

Processing

The product should be stored in a dry and cool place in the manufacturer's original packaging. The material can be processed using standard thermoplastic processing methods. Additional processing information is available in our Processing Guides which can be downloaded from our website www.hexpolTPE.com →

Processing temperatures (°C)	Injection Moulding	Extrusion
Cylinder	190 - 220	n.a.
Mould	15 - 50	n.a.
Predrying	Under normal conditions not necessary.	

Typical values are advisory and do not absolve customers from carrying out their own full-scale tests to determine the suitability of the material for the intended applications. Dryflex grades have an expected shelf life of minimum 12 months after shipment date. The product should be stored in a dry and cool place in the manufacturer's original packaging. Figures are indicative and may vary depending on the specific grade selected and the production site. HEXPOL TPE makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Dryflex® is a registered trademark, property of the HEXPOL Group of companies.