

TS150G6F2A

Property Data (产品物性表)

30%玻纤增强PA66, 无卤、无红磷阻燃, 注塑级产品。

Modified PA66 reinforced with 30% glass fiber, halogen and red phosphorus free flame retardant, for injection molding.

性能 (Properties)	测试标准 Test Methods	测试条件 Test Condition	单位 Units	典型值 Typical Value
Physical (物理属性)				
Density (密度)	ISO 1183	23°C	g/cm ³	1.44
Water Absorption (吸水率)	Sim.to ISO 62	60*60*2mm, water at 23°C, 24h	%	1.2
Rheological (流变性能)				
Molding Shrinkage (Parallel) 成型收缩率 (水平)	ISO 294-4	60*60*2mm	%	0.2-0.6
Molding Shrinkage (Normal) 成型收缩率 (垂直)	ISO 294-4	60*60*2mm	%	0.4-1.0
Mechanical (机械性能) 23°C, 50%RH				
Tensile Strength at Break (拉伸强度)	ISO 527-1/-2	20mm/min	MPa	140
Flexural Strength (弯曲强度)	ISO 178	5mm/min	MPa	200
Flexural Modulus (弯曲模量)	ISO 178	5mm/min	MPa	8500
Charpy Notched Impact Strength (简支梁缺口冲击强度)	ISO 179/1eA	23°C	kJ/m ²	8
Charpy Unnotched Impact Strength (简支梁无缺口冲击强度)	ISO 179/1eA	23°C	kJ/m ²	60
Thermal (热性能)				
Melting Temperature (熔点)	ISO 11357-1/-3	DSC, 10°C/min	°C	260
Heat Deflection Temperature (热变形温度)	ISO 75-1/-2	80*10*4mm, 1.8MPa	°C	235
Flammability (阻燃性能)				
Glow Wire Flammability Index (灼热丝燃烧指数)	IEC 60695-2-12	1.5mm	°C	960
Flammability UL 94 (阻燃性能)	UL 94	0.8mm	class	V-0
Electrical (电性能)				
Comparative Tracking Index (相对漏电起痕指数)	IEC 60112	3.0 mm	V	600
Surface Resistivity (表面电阻率)	IEC 60093	23°C	Ω	1.00E+13
Volume Resistivity (体积电阻率)	IEC 60093	23°C	Ω·m	5.00E+14
Processing (参考加工工艺)				
Drying Temperature (干燥温度)			°C	100-120
Suggested Max Moisture (水分要求)			%	≤0.1
Melting Temperature (熔体温度)			°C	265-290
Nozzle Temperature (喷嘴温度)			°C	275
Mold Temperature (模具温度)			°C	60-100
Injection Pressure (注射压力)			MPa	70-120
Injection Velocity (注射速度)			%	35-100

Notes: 备注

[1] These are typical properties only and are not to be construed as specifications.

该物性表数据仅是产品的典型值, 不能作为材料的技术指标。

[2] The processing parameters like processing temperature are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

参考加工工艺仅供产品注塑时参考使用, 可根据不同机型、不同模具以及产品要求, 对上述参数做适当调整。