Predicted crack onset (crosshead travel, force) vs the real first crack; PEEQ >= 0.043, s1 >= 50.5 MPa (100 %) or 42.9 MPa (85 %, potential)

case	PEEQ, raw	PEEQ, robust	s1 >= 100 %, raw	s1 >= 100 %, robust	potential: s1 >= 85 %, raw	site matches the real crack (observed)?
first: first nonlinear simulation (41,186 nodes, 33 % off)	0.59 mm, 1,685 N	0.70 mm, 1,905 N	1.67 mm, 2,819 N	1.92 mm, 2,877 N	1.43 mm, 2,719 N	85 %: no (nut-pocket corner); 100 %: no (nut-pocket corner)
before: what we started with (2,937 nodes, 33 % off)	0.98 mm, 2,535 N	1.05 mm, 2,633 N	1.76 mm, 3,162 N	1.86 mm, 3,193 N	1.50 mm, 3,045 N	85 %: no (prong inner side); 100 %: no (prong inner side)
stage2: learned test conditions, default mesh (2,937 nodes, 7.8 % off)	1.57 mm, 3,689 N	1.81 mm, 4,145 N	no break by 2.79 mm (42 MPa at the real crack)	no break by 2.79 mm (31.3 MPa at the real crack)	2.56 mm, 5,226 N	85 %: no (outer side); 100 %: no (outer side, most stressed)
stage3: learned conditions, pre-trained mesh (6,430 nodes, 4.6 % off)	1.22 mm, 2,837 N	1.37 mm, 3,181 N	2.58 mm, 5,045 N	no break by 2.79 mm (41.3 MPa at the real crack)	2.18 mm, 4,570 N	85 %: no (nut-pocket corner); 100 %: no (nut-pocket corner)
after: trained on the real test: most accurate mesh (8,753 nodes, 2.0 % off)	1.16 mm, 2,659 N	1.31 mm, 2,969 N	no break by 2.78 mm (43 MPa at the real crack)	no break by 2.78 mm (40.8 MPa at the real crack)	2.51 mm, 4,814 N	85 %: yes (lower inner bore); 100 %: yes (lower inner bore, most stressed)
real test: first crack	**2.51 mm, 4,755 N**	**2.51 mm, 4,755 N**	**2.51 mm, 4,755 N**	**2.51 mm, 4,755 N**	**2.51 mm, 4,755 N**	**lower inner bore (f5)**

Real crack site observed by the team on the broken part (no photo in the repo). Potential crack: tension at 85 % of the resin's dogbone strength (a margin for print defects and layer lines; the threshold was chosen after seeing this test).