

## Group 8 Test Parameter Summary

Material: Cobalt alloy 1233

Crosshead speed  $0.015 \pm 0.003$  mm/mm/min

Class B2 (ASTM E83) extensometer was used

5.0 mm diameter cylindrical specimen, 25 mm gage length

50 kN loadcell